

INDION® 222 Na NS

Non Solvent Cation

Description

INDION 222 Na NS is a golden yellow to brown coloured high capacity strongly acidic cation exchanger in bead form. It is based on cross linked polystyrene and has a gel structure. The resin contains sulphonic acid functional groups. It is supplied moist in the sodium form produced by solvent free process.

Applications

INDION 222 Na NS is used most widely in sodium form for water softening application. It can be used also in two-stage de-ionising as the cation exchanger in the hydrogen cycle. For potable water application, it is recommended to rinse the resin with 20 BV of water preferably DI water before putting it into use.

Characteristics

Appearance	:	Golden yellow to brown coloured beads
Matrix	:	Styrene divinylbenzene copolymer
Functional Group	:	Sulphonic acid
Ionic form as supplied	:	Sodium
Total exchange capacity	:	1.9 meq/ml, minimum
Moisture holding capacity	:	43 - 49 %
Shipping weight *	:	810 kg/m ³ , approximately
Particle size range	:	0.3 to 1.2 mm
> 1.2 mm	:	5.0%, maximum
< 0.3 mm	:	1.0%, maximum
Uniformity co - efficient	:	1.7, maximum
Effective size	:	0.45 to 0.55 mm
Treatment flow rate	:	5 - 40 bv/h
Operating pH range	:	0 to 14
Maximum operating temperature	:	140° C
Resistance to reducing agents	:	Good
Resistance to oxidizing agents	:	Generally good, chlorine should be absent
Organic extractives	:	1 mg/l maximum in de - ionised water
(As per USFDA 21 CFR 173.25)	:	1 mg/l maximum in 15% v/v ethanol solution
Impurities		
Iron	:	100 mg/l maximum as Fe
Heavy Metals	:	20 mg/l maximum as Pb
Arsenic	:	3 mg/l maximum as As

* Weight of resin, as supplied, occupying 1 m³ in a unit after backwashing and draining.

Packing

HDPE Lined bags	25/ 50 lts	LDPE bags	1 cft / 25 lts
Super sack	1000 lts	Super sack	35 cft
MS drums		Fiber drums	
with liner bags	180 lts	with liner bags	7 cft

Storage

Ion exchange resins require proper care at all times. The resin must never be allowed to become dry. Regularly open the plastic bags and check the condition

of the resin when in storage. If not moist, add enough clean demineralised water and keep it in completely moist condition. Always keep the resin drum in the shade. Recommended storage temperature is between 20°C and 40°C

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.



CONFORMANCE STATEMENT:

"Tested and certified by WQA against NSF/ANSI standard 61. See WQA website (www.wqa.org) for use instructions and limitations."

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark of Ion Exchange (India) Ltd.



CORPORATE OFFICE

Ion House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011
Tel: 022-3989 0909 Fax: 022-2493 8737
E-mail: ieil@ionexchange.co.in

INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 701
Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918
E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

REGIONAL OFFICES

- Chennai - Tel: 044-3989 0909/3910 2900 Fax: 044-2815 3361
E-mail: checro@ionexchange.co.in
- Delhi - Tel: 011-3989 0909/3054 3200 Fax: 011-2577 4837
E-mail: delcro@ionexchange.co.in
- Kolkata - Tel: 033-3989 0909/3043 3400 Fax: 033-2400 4345
E-mail: calcro@ionexchange.co.in
- Vashi - Tel: 022-3989 0909/3913 2300 Fax: 022-2788 9839
E-mail: mumcro@ionexchange.co.in

BRANCH OFFICES

- Bengaluru - Tel: 080-2204 2888
E-mail: bngcro@ionexchange.co.in
- Bhubaneswar - Tel: 0674-326 9525
E-mail: bbsr@ionexchange.co.in
- Chandigarh - Tel: 0172-274 5011 Fax: 0172-274 4594
E-mail: delcro@ionexchange.co.in
- Hyderabad - Tel: 040-3066 3101/02/03 Fax: 040-3066 3104
E-mail: hydcro@ionexchange.co.in
- Lucknow - Tel: 0522-319 99 11 Fax: 011-2577 4837
E-mail: lko.general@ionexchange.co.in
- Vadodara - Tel: 0265-302 7489/90 Fax: 0265-239 8508
E-mail: brdcro@ionexchange.co.in
- Visakhapatnam - Tel: 0891-324 6253
E-mail: sales.vizag@ionexchange.co.in

FACTORIES : Ankleshwar • Hosur • Patancheru • Rabale • Verna
ALL INDIA SERVICE AND DEALER NETWORK

Visit us at : www.ionindia.com