

INDION° 225 Na F

Description

INDION 225 NaF is a strongly acidic cation exchange resin containing sulphonic acid groups. It is specially designed for the treatment of foodstuffs, beverages, potable water and water used in the processing of food. Its specification is in compliance with the U.S. Food and Drug Administration Code of Federal Regulations section 21, paragraph 173.25, for use in the treatment of foods for human consumption. The resin is extremely robust and has excellent physical and chemical characteristics. It is supplied in moist condition in sodium form.

Characteristics

Arsenic

Appearance	:	Golden yellow to brown beads
Matrix	:	Styrene divinylbenzene copolymer
Functional Group	:	Sulphonic acid
Ionic form as supplied	:	Sodium
Total exchange capacity	:	2.0 meq/ml, minimum
Moisture holding capacity	:	43 - 50 %
Shipping weight *	:	830 kg/m³, approximately
Particle size range	:	0.3 to 1.2 mm
> 1.2 mm	:	5.0%, maximum
< 0.3 mm	:	1.0%, maximum
Uniformity co-efficient	:	1.7, maximum
Effective size	:	0.45 to 0.55 mm
Treatment flow rate	:	5 - 40 bv/h
Maximum operating temperature	:	140° C
Operating pH range	:	0 to 14
Resistance to reducing agents	:	Good
Resistance to oxidizing agents	:	Generally good, chlorine should be absent
Organic extractives	:	1 mg/l maximum in deionised water
(As per USFDA 21 CFR 173.25)		1 mg/l maximum in 15% v/v ethanol solution
Impurities		
Iron	:	100 mg/l maximum as Fe
Heavy Metals	:	20 mg/l maximum as Pb

: 3 mg/l maximum as As

* Weight of resin, as supplied, occupying 1 m3 in a unit after backwashing and draining.

Recommended usage

It is highly recommended that the INDION 225NaF after charging in the service vessel should be thoroughly washed with 20 bv* of deionised water, to ensure that the organic leachables are well within the limits. It may be noted that this procedure is to be carried out only after initial charge or in case the service vessel is out of operation for a long period.

* 1 bv = 1 m^3 per m^3 of resin volume

Storage

INDION 225 NaF resin beads must never be allowed to become dry. Therefore always store resin bags in the shade.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

Packing

HDPE Lined bags	25/ 50 lts	LDPE bags	1 cft / 25 lts
Super sack	1000 lts	Super sack	35 cft
MS drums		Fiber drums	
with liner bags	180 lts	with liner bag	gs 7 cft



CONFORMANCE STATEMENT:

This product conforms to NSF / ANSI Standard 61 and is certified with GOLD SEAL from WQA

INDION range ot Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark of Ion Exchange (India) Ltd.

COMPANSE INTERCEPTION EXCHANGE Refreshing the Planet

CORPORATE OFFICE

Ion House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011 Tel: 022-3989 0909 Fax: 022-2493 8737 E-mail: ieil@ionexchange.co.in

INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 701 Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918 E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

REGIONAL OFFICES

• Chennai	- Tel: 044-3989 0909/3910 2900 E-mail: checro@ionexchange.co.in	Fax: 044-2815 3361
• Delhi	- Tel: 011-3989 0909/3054 3200 E-mail: delcro@ionexchange.co.in	Fax: 011-2577 4837
• Kolkata	- Tel: 033-3989 0909/3043 3400 E-mail: calcro@ionexchange.co.in	Fax: 033-2400 4345
• Vashi	- Tel: 022-3989 0909/3913 2300 E-mail: mumcro@ionexchange.co.i	Fax: 022-2788 9839 n

BRANCH OFFICES

• Bengaluru	⁻ Tel: 080-2204 2888 E-mail: bngcro@ionexchange.co.in				
• Bhubaneswar	⁻ Tel: 0674-326 9525 E-mail: bbsr@ionexchange.co.in				
• Chandigarh	- Tel: 0172-274 5011 E-mail: delcro@ionexchange.c	Fax: 0172-274 4594 co.in			
• Hyderabad	- Tel: 040-3066 3101/02/03 E-mail: hydcro@ionexchange.				
• Lucknow	- Tel: 0522-301 3401/02 E-mail: luk.general@ionexcha				
• Vadodara	- Tel: 0265-302 7489/90 E-mail: brdcro@ionexchange.				
• Visakhapatnam	- Tel: 0891-324 6253 E-mail: sales.vizag@ionexchar	nge.co.in			
FACTORIES : Ankleshwar • Hosur • Patancheru • Rabale • Verna					
ALL INDIA SERVICE AND DEALER NETWORK					