

INDION® 830

Description

INDION 830 is a strong base type I anion exchange resin having quaternary ammonium functional groups. It is based on crosslinked polystyrene and has a macroporous structure. INDION 830 possesses highly porous structure which is capable of absorbing and desorbing organic material. INDION 830 is supplied and used in chloride form to scavenge organic molecules of medium to high molecular weight. It is operated in the salt cycle using warm brine as the regenerant. Its resistance to organic fouling is superior

to gel type resins because of its large pore structure.

INDION 830 has high osmotic and thermal shock resistance.

INDION 830 can be used to remove tannins from both industrial and residential water supplies. As an organic scavenger INDION 830 can be used prior to demineraliser using brine as a regenerant. INDION 830 can also be placed in the same vessel with INDION 225 Na using the same brine regenerant. INDION 830 will stay in place because of the difference in densities between the two resins.

Characteristics

Appearance	:	Off white to brown opaque beads
Matrix	:	Styrene divinylbenzene copolymer
Functional Group	:	Quaternary ammonium
Ionic form as supplied	:	Chloride
Total exchange capacity	:	0.95 meq/ml, minimum
Moisture holding capacity	:	57 - 66 %
Shipping weight *	:	640 - 700 kg/m ³ , approximately
Particle size range	:	0.3 to 1.2 mm
> 1.2 mm	:	5.0%, maximum
<0.3 mm	:	1.0%, maximum
Uniformity co-efficient	:	1.7, maximum
Effective size	:	0.45 to 0.60 mm
Maximum operating temperature	:	80° C
Operating pH range	:	4 to 10 for organic removal
Resistance to reducing agents	:	Good
Resistance to oxidizing agents	:	Generally good, chlorine should be absent

* Weight of resin, as supplied, occupying 1 m³ in a unit after backwashing and draining.

Packing

HDPE Lined bags	25/ 50 lts	LDPE bags	1 cft / 25 lts
Super sack	1000 lts	Super sack	35 cft
MS drums		Fiber drums	
with liner bags	180 lts	with liner bags	7 cft

Storage

Ion exchange resins require proper care at all times. The resins must never be allowed to become dry. Regularly open the plastic bags and check the condition of the resin when in storage.

If not moist, add enough clean demineralised water and keep it in completely moist condition. Always keep the resin drum in the shade. Recommended storage temperature is between 20°C and 40°C.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety pre-cautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark of Ion Exchange (India) Ltd.



ION EXCHANGE (INDIA) LTD.

Corporate Office

Ion House, Dr. E. Moses Road, Mahalaxmi,
Mumbai - 400011 | Tel: +91 22 6231 2000
E-mail: ieil@ionexchange.co.in

Regional and Branch Offices - [CLICK HERE](#)

Bengaluru | Bhubaneswar | Chandigarh | Chennai | Delhi
Hyderabad | Kolkata | Lucknow | Vadodara | Vashi
Visakhapatnam

International Division

R-14, T.T.C MIDC, Thane - Belapur Road, Rabale,
Navi Mumbai - 400 701 | Tel: +91 22 6857 2400
E-mail: export.sales@ionexchange.co.in

Overseas Offices - [CLICK HERE](#)

Bahrain | Bangladesh | Canada | Indonesia | Kenya
Malaysia | Oman | Saudi Arabia | Singapore | South Africa
Sri Lanka | Tanzania | Thailand | UAE | USA

Manufacturing Units

India - Ankleshwar | Hosur | Patancheru | Rabale | Verna | Wada

Overseas - Hamriyah | Kingdom of Bahrain | Indonesia | Bangladesh

All India Service and Dealer Network

www.ionindia.com

